

## Chrome 99.5%

<b>Material</b>	Chromium powder		
<b>Formula</b>	Cr		
<b>Appearance</b>	Metallic grey; powder or granules		
<b>Melting point</b>	1907 °C		
<b>Boiling point</b>	2672 °C		
<b>Size</b>	US Standard ASTM E11 Size range from -12 mesh to -260 mesh Specific sizing as per customer requirements		
<b>Chemical composition:</b>	<b>Element</b>	<b>Min %</b>	<b>Max %</b>
	Chromium*	99.5	-
	Iron	-	0.050
	Oxygen	-	0.050
	Nitrogen	-	0.002
	Sulphur	-	0.010
	Carbon	-	0.005
	Aluminium	-	0.001
	Copper	-	0.005
	* Chromium reported on metallic content only		
<b>Packing</b>	Steel drums with sealed polyethylene liner		
<b>Further information</b>	Global Metal Powders tailors production to fulfil customer requirements. Please contact us with any specific technical requests.		



### Chrome 99.5%

<b>Material</b>	Chromium powder		
<b>Formula</b>	Cr		
<b>Appearance</b>	Metallic grey; powder or granules		
<b>Melting point</b>	1907 °C		
<b>Boiling point</b>	2672 °C		
<b>Size</b>	US Standard ASTM E11 Size range from -12 mesh to -325 mesh Specific sizing as per customer requirements		
<b>Chemical composition:</b>	<b>Element</b>	<b>Min %</b>	<b>Max %</b>
	Chromium*	99.5	-
	Iron	-	0.05
	Oxygen	-	0.05
	Nitrogen	-	0.002
	Sulphur	-	0.01
	Carbon	-	0.005
	Aluminium	-	0.001
	Copper	-	0.0005
	* Chromium reported on metallic content only		
<b>Packing</b>	Steel drums with sealed polyethylene liner		
<b>Further information</b>	Global Metal Powders tailors production to fulfil customer requirements. Please contact us with any specific technical requests.		