

Chrome 99.5%

Material	Chromium powder		
Formula	Cr		
Appearance	Metallic grey; powder or granules		
Melting point	1907 °C		
Boiling point	2672 °C		
Size	US Standard ASTM E11 Size range from -12 mesh to -260 mesh Specific sizing as per customer requirements		
Chemical composition:	Element	Min %	Max %
	Chromium*	99.5	-
	Iron	-	0.050
	Oxygen	-	0.050
	Nitrogen	-	0.002
	Sulphur	-	0.010
	Carbon	-	0.005
	Aluminium	-	0.001
	Copper	-	0.005
	* Chromium reported on metallic content only		
Packing	Steel drums with sealed polyethylene liner		
Further information	Global Metal Powders tailors production to fulfil customer requirements. Please contact us with any specific technical requests.		



Chrome 99.95%

Material	Chromium powder		
Formula	Cr		
Appearance	Metallic grey; powder or granules		
Melting point	1907 °C		
Boiling point	2672 °C		
Size	US Standard ASTM E11 Size range -325 mesh Specific sizing as per customer requirements		
Chemical composition:	Element	Min %	Max %
	Chromium*	99.95	-
	Iron	-	0.030
	Oxygen	-	0.050
	Nitrogen	-	0.002
	Sulphur	-	0.010
	Carbon	-	0.005
	Aluminium	-	0.001
	Copper	-	0.0005
	* Chromium reported on metallic content only		
Packing	Steel drums with sealed polyethylene liner		
Further information	Global Metal Powders tailors production to fulfil customer requirements. Please contact us with any specific technical requests.		

Chrome 99.95%

Material	Chromium powder		
Formula	Cr		
Appearance	Metallic grey; powder or granules		
Melting point	1907 °C		
Boiling point	2672 °C		
Size	US Standard ASTM E11 Size range from -12 mesh to -260 mesh Specific sizing as per customer requirements		
Chemical composition:	Element	Min %	Max %
	Chromium*	99.95	-
	Iron	-	0.010
	Oxygen	-	0.010
	Nitrogen	-	0.002
	Sulphur	-	0.010
	Carbon	-	0.005
	Aluminium	-	0.001
	Copper	-	0.0005
	* Chromium reported on metallic content only		
Packing	Steel drums with sealed polyethylene liner		
Further information	Global Metal Powders tailors production to fulfil customer requirements. Please contact us with any specific technical requests.		

Chrome 99.95%

Material	Chromium powder		
Formula	Cr		
Appearance	Metallic grey; powder or granules		
Melting point	1907 °C		
Boiling point	2672 °C		
Size	US Standard ASTM E11 Size range from -12 mesh to -325 mesh Specific sizing as per customer requirements		
Chemical composition:	Element	Min %	Max %
	Chromium*	99.95	-
	Iron	-	0.01
	Oxygen	-	0.01
	Nitrogen	-	0.002
	Sulphur	-	0.01
	Carbon	-	0.005
	Aluminium	-	0.001
	Copper	-	0.0005
	* Chromium reported on metallic content only		
Packing	Steel drums with sealed polyethylene liner		
Further information	Global Metal Powders tailors production to fulfil customer requirements. Please contact us with any specific technical requests.		