

Molybdenum 99.8%

Material	Molybdenum powder.		
Formula	Mo		
Appearance	Metallic grey; powder or granules		
Melting point	2623 °C		
Boiling point	4639 °C		
Size	US Standard ASTM E11 Size range from -12 mesh to -325 mesh Specific sizing as per customer requirements		
Chemical composition:	Element	Min %	Max %
	Molybdenum*	99.8	-
	Iron	-	0.050
	Oxygen	-	0.050
	Nitrogen	-	0.010
	Sulphur	-	0.005
	Carbon	-	0.005
	Aluminium	-	0.001
	Copper	-	0.005
	* Molybdenum reported on metallic content only		
Packing	Steel drums with sealed polyethylene liner		
Further information	Global Metal Powders tailors production to fulfil customer requirements. Please contact us with any specific technical requests.		

Molybdenum 99.8%

Material	Molybdenum powder.		
Formula	Mo		
Appearance	Metallic grey; powder or granules		
Melting point	2623 °C		
Boiling point	4639 °C		
Size	US Standard ASTM E11 Size range from -12 mesh to -325 mesh Specific sizing as per customer requirements		
Chemical composition:	Element	Min %	Max %
	Molybdenum*	99.8	-
	Iron	-	0.050
	Oxygen	-	0.050
	Nitrogen	-	0.010
	Sulphur	-	0.005
	Carbon	-	0.005
	Aluminium	-	0.001
	Copper	-	0.005
	* Molybdenum reported on metallic content only		
Packing	Steel drums with sealed polyethylene liner		
Further information	Global Metal Powders tailors production to fulfil customer requirements. Please contact us with any specific technical requests.		